

# PRODUCTS.

INTERIORS

## Distributore Esclusivo



**RANCATI**  
Tessuti e Accessori per la Nautica

Rancati Srl  
Via Molo Giano Molo Guardiano  
16128 Genova  
☎ +39 010 2467781 - 📠 +39 010 2467780






[www.rancatinautica.com](http://www.rancatinautica.com)  
[info@rancatinautica.com](mailto:info@rancatinautica.com)

**ALCANTARA®**  
EXTRAORDINARY EVERY DAY

# PRODUCTS.

## INTERIORS

### WASHING INSTRUCTION

						
Alcantara® Bord FR 5353*	•	•	•	•	•	
Alcantara® Avant 5366*	•	•	•	•	•	
Alcantara® Bord 5015	•	•	•	•	•	•
Alcantara® Tugas 5111	•	•	•	•	•	•
Alcantara® Tender 5130	•	•	•	•	•	•
Alcantara® Colorado 5140	•	•	•	•	•	•
Alcantara® Domino 5410	•	•	•	•	•	•
Alcantara® Domino BS 5510	•	•	•	•	•	•
Alcantara® Starlite FR 3530			•	•	•	•
Alcantara® Starlite 6430			•	•	•	•

\* Flame retardant version



UNI EN ISO 9001:2008  
Management System certification



UNI EN ISO 14001:2004  
Management System certification



Management System certification



Management System certification



Our products have the Oeko-Tex "standard 100" certification - only valid for the not flame retardant versions.



Tested for harmful substances according to Oeko-Tex Standard 100



Alcantara® Bord FR 5353

FR CONTENT	38 ± 2 % (*)		
THICKNESS	0.73 ÷ 0.93 mm		
UNITWEIGHT	UNI EN 29073 - 1	≥ 275 g/m <sup>2</sup>	
WIDTH	≥ 142 N		
BREAKING LOAD	lengthwise	UNI EN 29073 - 3	≥ 225 N
	trasversal	UNI EN 29073 - 3	≥ 175 N
FLAME RESISTANCE	Walls	CSE RF 2/75/A RF 3/77	Class 1
	Curtains	CSE RF 1/75/A RF 3/77	Class 1
COLOR FASTNESS (**)			
TO LIGHT	UNI EN ISO 105 - B02	≥ 5 blue scale (1-5)	
TO DOMESTIC WASHING	tone change	UNI EN ISO 105 - C06	≥ 4 grey scale (1-5)
	staining	UNI EN ISO 105 - C06	≥ 3 white scale (1-5)
TO RUBBING	dry	UNI EN ISO 105 - X12	≥ 4 white scale (1-5)
	wet	UNI EN ISO 105 - X12	≥ 3 white scale (1-5)

(\*) Referred to Alcantara®. (\*\*) Due to the process technology, shade variations may occur.



Alcantara® Tender 5130

THICKNESS	≥ 0.95 mm	
UNIT WEIGHT	UNI EN 29073 - 1	≥ 340 g/m <sup>2</sup>
WIDTH	≥ 142 cm	
DIMENSIONAL STABILITY (WATER 40°C)	UNI EN 25077 + UNI EN ISO 6330	≤ 4 %
BREAKING LOAD	lengthwise	UNI EN 29073 - 3 ≥ 750 N
	trasversal	UNI EN 29073 - 3 ≥ 400 N
ELONGATION AT 50 N	lengthwise	UNI EN 29073 - 3 ≤ 8%
	trasversal	UNI EN 29073 - 3 ≤ 10%
TEARING RESISTANCE	UNI EN ISO 13937-3	≥ 30 N
MARTINDALE ABRASION	UNI EN ISO 12947 - 1	≥ 30000 cycles (**)
	End point	UNI EN ISO 12947 - 2 ≥ 150000 cycles
COESION	UNI EN ISO 2411	≥ 15 N
SEWING RESISTANCE	internal method	≥ 300 N
COLOR FASTNESS (***)		
TO LIGHT	UNI EN ISO 105 - B02	≥ 5 blue scale (1-8)
TO DOMESTIC WASHING	tone change	UNI EN ISO 105 - C06 ≥ 4 grey scale (1-5)
	staining	UNI EN ISO 105 - C06 ≥ 3 white scale (1-5)
TO DRY CLEANING	tone change	UNI EN ISO 105 - D01 ≥ 4 grey scale (1-5)
TO RUBBING	dry	UNI EN ISO 105 - X12 ≥ 4 white scale (1-5)
	wet	UNI EN ISO 105 - X12 ≥ 3 white scale (1-5)

(\*) Without backing. (\*\*) Slight change in the appearance of product surface. (\*\*\*) Due to the process technology, shade variations may occur.



**Alcantara® Tugan 5111**

THICKNESS			≥ 3 mm
UNIT WEIGHT		UNI EN 29073 - 1	≥ 370 g/m <sup>2</sup>
WIDTH			≥ 142 cm
BREAKING LOAD	lengthwise	UNI EN 29073 - 3	≥ 225 N
	trasversal	UNI EN 29073 - 3	≤ 175 N
FLAME RESISTANCE		CSE RF 2/75/A RF 3/77	Class 1
COLOR FASTNESS (**)			
TO LIGHT		UNI EN ISO 105 - B02	≥ 5 blue scale (1-8)
TO RUBBING	dry	UNI EN ISO 105 - X12	≥ 4 white scale (1-5)
	wet	UNI EN ISO 105 - X12	≥ 3 white scale (1-5)

(\*) Referred to Alcantara®. (\*\*) Due to the process technology, shade variations may occur.